

ITEM	SPECIFICATION
------	---------------

TECHNICAL SPECIFICATIONS

Dimensions	Plank: Width: 7.31" (185mm), Length: 48" (1,219 mm) Tile: Width: 12" (305mm), Length: 24" (610 mm)
Thickness	Overall: 0.12" (3mm) Wear Layer: 0.55 mm (22mil)
Profile	Micro-Bevel Edges
Coverage	Plank: 39 sq.ft (3.62 sq.m) per box, 1,950 sq.ft (181.2 sq.m) per pallet Tile: 36 sq.ft (3.34 sq.m) per box, 1,800 sq.ft (167.2 sq.m) per pallet
Planks per Box	Plank: 17 Planks Tile: 18 Planks
Boxes per Pallet	Plank: 50 Boxes Tile: 50 Boxes
Weight	Plank: 35.1 lbs. (15.9 kg) per box, 1,755 lbs. (796 kg) per pallet Tile: 32 lbs. (14.5 kg) per box, 1,600 lbs. (726 kg) per pallet
Type & Composition	100% Virgin Hardened Vinyl Core
Application	Residential & Commercial
Surface Treatment	4x UV Coating, anti-microbial embedded with Ceramic bead Finish
Visual Pattern Repeat	Approx. every 1,200mm (39.37in)
Print pattern repeat	Approx. 1 plank in every 10 boxes
Backing	Dry Back
Warranty	10 Year Limited Commercial 25 Year Limited Residential

PERFORMANCE

Dimensional Stability	.0038% inch/foot	ASTM F2199	Stain & Chemical Resistance	0: 95% Ethyl Alcohol, Cement Paste, 10% Ammonium hydroxide, Kerosene, Sesame Oil, Soy Sauce, Soy Bean Oil, Lubricant, Coffee, Tea, Ketchup. 1: Nitric Acid, Sulfuric Acid 95%. 2: Acetone, Nail Polish Remover, Methylene Chloride. KSM 3802—24 Hr. Exposure
Sound Absorption RATING	48/54	IIC RATING/STC	Smoke Density - Flaming	280 (Corrected to Max Density) ASTM E662
Use with Underfloor Radiant Heating		Recommended	Smoke Density - Non-Flaming	417 (Corrected to Max Density) ASTM E662
Floorscore	Certified		Short Term Indentation 0.008"	ASTM F1914
Emmissions after 28 days		≤0.005 parts/million	Static Load 1,000 PSI	
Critical Radiant Flux	0.99 watts/cm2	ASTM E648-06	0.008" of Residual Indentation	ASTM F970
Pass		Mekol Burner Test	Static Coefficient of Friction	Dry: 0.60 ASTM D2047 Dry: 0.7144 ASTM C1028 Wet: 0.8900
Light Resistance	6.0	ASTM F1515	Rolling Chair	Negligible Disturbance ATSM F2753
Heat Stability	4.3	ASTM 1514		
Slip Resistance R=10 (Meets Commercial Standard)		AS 4586 (CSIRO)		
Walking Angle	16°			
ADA	Exceeds ADA Requirements			
Deflection	55.29 mm	ASTM F1304		
Abrasion Resistance	0.003% @ 1,000 Cycles	ASTM D3884		



LUCIDA[®]
SURFACES

setting life's stage™

Lucida Surfaces USA

55 Haul Road
Wayne, NJ 07470
+1 (845) 877-7008

Lucida Surfaces Canada

8620 Rue Pascal-Gagnon
Montreal QC H1P 1Z1
+ (514) 587-9926

LucidaSurfaces.com